



Technical Bulletin

2400 Boston Street, Suite 200, Baltimore, Maryland 21224
Phone: 410-675-2100 or 800-543-3840

Revised: 06/10/2019

MONO[®] Acoustical Sealant

- For use in sound transmission and sealing wall penetrations
- Easy to gun
- Single-component
- Long lasting
- Excellent adhesion
- Does not stain or bleed
- Remains flexible
- Non-skinning

Packaging: 295mL and 825mL cartridges,
Colours: Dark Grey
UPC Number: 7079875400, 7079875401

Company Information:

Manufactured for: DAP Canada, 475 Finchdene Square, Unit 5, Scarborough, ON. M1X 1B7
Usage Information: Call 888-DAP-TIPS or visit dap.ca & click on “Ask the Expert”
Order Information: 800-327-3339
Fax Number: 410-558-1068
Also visit the DAP website at dap.ca

Product Description:

MONO[®] Acoustical Sealant is a single-component, non-skinning, non-hardening synthetic butyl rubber sealant for use in reducing sound transmission in drywall partitions and for sealing wall penetrations. Provides an effective adhesive seal for air and vapour barriers. MONO[®] Acoustical Sealant meets CAN/CGSB 19.21 M87 specifications.

Surface Preparation & Application:

1. All surfaces must be clean, dry and completely free of old caulk.
2. Trim nozzle at 30° angle to desired bead size.
3. Puncture inner seal at the base of the nozzle.
4. Load into caulking gun.
5. Fill joint with sealant, pushing sealant ahead of nozzle.

For best results:

- Apply in temperatures above 5°C (40°F).
- This product is intended for captive applications only. It is not to be used for exposed interior applications as the product does not cure and will track on interior finishes.
- Not recommended for exterior applications.

- *Joint size should not exceed 20 mm x 13 mm (3/4" x 1/2"). Parallel beads of sealant may be applied to double layer drywall partition assembly to increase sound deadening.*
- *Store sealant away from extreme heat or cold.*

Typical Physical & Chemical Characteristics:

Tooling Time:	Indefinite, material does not skin or cure
Tack-Free Time:	Remains pliable, does not become tack free
Paintable:	Not paintable
Odour:	Naphtha
Consistency:	Non-sag, gunnable paste
Vehicle:	Rubber
Volatile Weight:	9%
Flash Point:	Not established
Filler:	Mineral extender
Specific Gravity:	.69
Solids:	91%
Density:	1690 kg/m ³ (14.1 lbs/gallon)
Temperature Service Range:	-40°C to 115°C (-40°F to 240°F)
Temperature Application Range:	5°C to 35°C (40°F to 95°F)
Freeze Thaw Stability:	Stable
Shelf Life:	12 months
Coverage (825 mL cartridge):	Approx.–26m (85 linear ft.) of a 6.35mm (1/4") bead
SDS No:	00042435604

Clean Up:

Immediately remove all excess sealant or smears adjacent to joint edges as work progresses using xylene or mineral spirits. Any utensils used for tooling can also be cleaned with xylene or mineral spirits. Do not use xylene or mineral spirits to clean skin.

Safety & Warranty Information:

See product label and Safety Data Sheet (SDS) for health and safety information.

For an SDS, contact your supplier or visit dap.ca

If product fails to perform as directed, within one year from the date of purchase, call 1-888-DAP-TIPS, with your sales receipt and product container available, for replacement product or sales price refund.

DAP will not be liable for incidental or consequential damages.