

DAP® HVAC Professional 100% RTV Silicone Sealant

PRODUCT DESCRIPTION

DAP® HVAC SILICONE is a high-performance sealant designed especially for HVAC applications. Provides a long-lasting weather resistant seal with supreme adhesion, flexibility, and durability. Adheres to most common building materials and remains flexible from -40°C to 246°C. Meets Fed. Spec. TT-S001543A, ASTM C920, FDA Reg. No. 21 CFR 177.2600, and NSF/ANSI Standard 51. Safe for incidental food contact. Interior/exterior use.



| PACKAGING | COLOR | UPC |
|-----------|----------|------------|
| 300 mL | White | 7079874328 |
| 300 mL | Clear | 7079874327 |
| 300 mL | Aluminum | 7079874326 |

KEY FEATURES & BENEFITS

- 100% RTV silicone
- Remains flexible up to 246°C
- Will not crack or shrink
- 100% waterproof/weather resistant seal
- Meets Fed. Spec. TT-S001543A and ASTM C920
- Certified by NSF to NSF/ANSI Standard #51
- It is safe for incidental food contact. When cured and washed, the product meets FDA Reg 21, CFR 177.2600
- Interior/exterior use

SUGGESTED USES

USE FOR:

- Air conditioners
- Ducts
- Furnaces
- Access doors

- Refrigerators
- Aluminum siding
- Flanged pipe joints
- Window & door frames
- Vents
- Pipes
- Flues

5/21/2021

ADHERES TO:

- Most metals*
- Ceramic
- Porcelain
- Marble

- Non-oily surfaces
- Glass
- Fiberglass
- Most plastics
- *Not recommended for use on or near brass, copper or copper alloys, zinc, iron, galvanized metals or other surfaces prone to attack by weak acids.
- Painted surfaces
- Most common building materials

FOR BEST RESULTS

- Application temperature range is between -18°C to 38°C.
- Not recommended for continuous underwater use, filling butt joints, surface defects, tuck-pointing, chimneys, stovepipes or fireplace applications. Not recommended for structural glazing.
- Not for oily woods or cementitious surfaces. Substrates made of methylmethacrylate, polycarbonate, polypropylene, polyethylene and polytetrafluroethylene do not allow for best adhesion and compatibility with sealant. Try test area before using.
- Corrodes some metals.
- Not paintable. Paint surface substrate before applying sealant.
- Store below 26°C in dry place for optimal shelf life.

APPLICATION

Surface Preparation

Surface must be clean, dry, structurally sound and free of all foreign material.

Product Application

- 1. Cut nozzle at a 45° angle to desired bead size.
- 2. Puncture inner foil seal.
- 3. Load into caulk gun.
- 4. Fill gap or crack with sealant.
- 5. If necessary, tool or smooth the bead of sealant with a finishing tool before the sealant skins over.
- 6. Clean up excess wet sealant from surface and tools with mineral spirits. Scrape or cut away excess dried sealant. Do not use mineral spirits to clean skin. Wash skin with soap and water.
- 7. Reseal cartridge for storage and reuse.

2400 Boston Street |Suite 200 | Baltimore, MD | 21224

TYPICAL PHYSICAL & CHEMICAL PROPERTIES

| Typical Uncured Physical Properties | | |
|--------------------------------------|--|--|
| Appearance/Consistency | Gunnable, non-sag paste | |
| Base Polymer | Silicone rubber | |
| Filler | Not applicable | |
| Volatile | Not applicable | |
| Weight % Solids | >97.0% | |
| Specific Gravity | 1.01 | |
| Odor | Vinegar-like | |
| Flash Point | >100°C | |
| Freeze Thaw Stability (ASTM C1183) | Will not freeze | |
| Shelf Life | 24 months | |
| Coverage | 15.5 linear metres at 5 mm bead size | |
| | | |
| Typical Application Properties | | |
| Application Temperature Range | -18°C to 38°C | |
| Tooling Time (Working Time) | 10 minutes | |
| Tack Free Time | 15 minutes | |
| Full Cure | 24 hours | |
| Return to Service Time | 12 hours | |
| Vertical Sag (ASTM D2202) | 1.5 mm | |
| Typical Cured Performance Properties | | |
| Service Temperature Range | -40°C to 246°C | |
| Water Ready Time | 12 hours | |
| Paint Ready Time | Not paintable | |
| Mildew Resistance | Cured sealant is mold & mildew resistant | |
| Dynamic Joint Movement (ASTM C719) | +/- 25% | |

2400 Boston Street |Suite 200 | Baltimore, MD | 21224

CLEAN UP & STORAGE

Remove excess uncured sealant from surfaces and tools with mineral spirits. Excess cured sealant must be cut or scraped away. Do not use mineral spirits to clean skin. Wash skin with soap and water. Store container in temperatures below 80°F and in a dry place.

SAFETY

See product label or Safety Data Sheet (SDS) for health and safety information. You can request a SDS by visiting our website at dap.com or calling **888-327-8477**.

WARRANTY

DAP Canada, DAP Products Inc. and their respective affiliates will not accept liability for more than replacement product or sales price refund under any circumstances.

COMPANY IDENTIFICATION

Manufactured for: DAP Canada, 475 Finchdene Square, Unit 5, Scarborough, ON, M1X 1B7

Usage Information: Call 888-DAP-TIPS or visit dap.ca & click on "Ask the Expert"

Order Information: 800-668-9397 or 416-321-1522

Fax Number: 416-321-3325

Also visit the DAP website at dap.ca